



## Alloys 316 / 316L (UNS S31600 / UNS S31603)

Grade 316 is the standard molybdenum-bearing grade, second in overall volume production to 304 amongst the austenitic stainless steels. The molybdenum gives 316 better overall corrosion resistant properties than Grade 304, particularly higher resistance to pitting and crevice corrosion in chloride environments.

Grade 316L, the low carbon version of 316 and has very high immunity from sensitization (grain boundary carbide precipitation). It is extensively used in the oil and gas and chemical industries for its cost effective corrosion resistance and ease of fabrication. There is commonly no appreciable price difference between 316 and 316L stainless steel. The austenitic structure also gives these grades excellent toughness, even down to cryogenic temperatures. Compared to chromium-nickel austenitic stainless steels, 316L stainless steel offers higher creep, stress to rupture and tensile strength at elevated temperatures.

These alloys may be considered for a wide variety of applications where one or more properties are important.

### AVAILABLE TUBE PRODUCT FORMS

STRAIGHT | COILED | SEAMLESS

SEAM WELDED AND COLD REDRAWN

SEAM WELDED, COLD REDRAWN AND ANNEALED

### TYPICAL MANUFACTURING SPECIFICATIONS

ASTM A213      ASTM A632

ASTM A269      BS EN 10216 Pt 5

ASTM A312

Also individual customer specifications.

### TYPICAL APPLICATIONS

PROCESS ENGINEERING

CONTROL LINES

HIGH PERFORMANCE LIQUID CHROMATOGRAPHY (HPLC)

HEAT EXCHANGERS

CONDENSERS

SEMICONDUCTORS

MEDICAL IMPLANTS (INCLUDING PINS, SCREWS AND IMPLANTS)

### INDUSTRIES PREDOMINANTLY USING THIS GRADE

OIL AND GAS      HIGH PERFORMANCE

CHEMICAL PROCESSES      COMMERCIAL



## Technical Data

### MECHANICAL PROPERTIES

Temper	Annealed			Cold worked (approx. 20%)		
	316	316L		316	316L	
Material	316	316L		316	316L	
Tensile Rm	75	70	ksi (min)	102 - 131		ksi (min)
Tensile Rm	515	485	MPa (min)	700 - 900		MPa (min)
R.p. 0.2% Yield	30	27	ksi (min)	73 - 102		ksi(min)
R.p. 0.2% Yield	205	182	MPa (min)	500 - 700		MPa (min)
Elongation (2" or 4D gl)	35		% (min)	40		% (min)

### PHYSICAL PROPERTIES (Room Temperature)

Specific Heat (0-100°C)	500	J.kg <sup>-1</sup> .°K <sup>-1</sup>
Thermal Conductivity	16.3	W.m <sup>-1</sup> .°K <sup>-1</sup>
Thermal Expansion	15.9	mm/m/°C
Modulus Elasticity	193	GPa
Electrical Resistivity	7.4	μohm/cm
Density	7.99	g/cm <sup>3</sup>

### CHEMICAL COMPOSITION

(% by weight)

Element	316		316L	
	Min	Max	Min	Max
C	-	0.08	-	0.035
Mn	-	2	-	2
Ni	10	14	10	15
Cr	16	18	16	18
Mo	2	3	2	3
S	-	0.03	-	0.03
Si	-	1	-	1
P	-	0.045	-	0.045